

Methods for

# Analysis and testing of coal and coke —

Part 110: Size analysis of coke —

Section 110.2 Nominal top size 20 mm or  
less

ICS:75.160.10

UDC 662.749.2:620.168.32

# Committees responsible for this British Standard

The preparation of this British Standard was entrusted to Technical Committee SFI/3, Analysis and testing of coal and coke, upon which the following bodies were represented:

British Cement Association  
 British Coal Corporation  
 British Gas plc  
 British Steel Industry  
 Electricity Association  
 GAMBICA (BEAMA Ltd.)  
 Power Generation Contractors' Association [PGCA (BEAMA Ltd.)]

This British Standard, having been prepared under the direction of the Sector Board for Materials and Chemicals, was published under the authority of the Standards Board and comes into effect on 15 May 1996

© BSI 07-1999

The following BSI references relate to the work on this standard:  
 Committee reference SFI/3  
 Draft announced in *BSI News* January 1996

ISBN 0 580 25525 5

## Amendments issued since publication

Amd. No.	Date	Comments

---

# Contents

	Page
Committees responsible	Inside front cover
National foreword	ii
<hr/>	
1 Scope and field of application	1
2 References	1
3 Principle	1
4 Apparatus	1
5 Sample	1
6 Procedure	2
7 Expression of results	2
8 Test report	3
<hr/>	
List of references	Inside back cover

# National foreword

This British Standard has been prepared by SFI/3 and is identical to ISO 2325:1986 *Coke — Size analysis — (Nominal top size 20 mm or less)*, published by the International Organization for Standardization (ISO) and in the preparation of which the United Kingdom played a full part.

In conjunction with BS 1016-110.1 this British Standard is a revision of BS 1016-18:1981 which is withdrawn. The main changes in this revision are the separation of the methods for “small” and “large” coke, and a more precise description of the sieving procedure.

BS 1016-110.2 is part of a rationalized and restructured BS 1016. The Parts numbered from 1 to 21 are gradually being withdrawn and replaced by Parts in the new series. The full list of Parts in the new series, together with corresponding numbering of the old series and related ISO standards is given in BS 1016 *Analysis and testing of coal and coke Part 100:1994 General introduction and methods for reporting results*.

## Cross-references

International standard	Corresponding British Standard
ISO 579:1981	BS 1016 <i>Methods for analysis and testing of coal and coke Part 2:1973 Total moisture of coke</i> (Technically equivalent)
ISO 1953:1994	Part 109:1995 <i>Size analysis of coal</i> (Identical)
ISO 2591 <sup>a</sup>	BS 1796 <i>Test sieving</i> (Identical)

<sup>a</sup> ISO 2591:1973 has been superseded by ISO 2591-1:1988.

The Technical Committee has reviewed the provisions of ISO 565, ISO 2309, and ISO 3310 to which reference is made in the text, and has decided that they are acceptable for use in conjunction with this standard.

A British Standard related to ISO 2309:1980 is BS 1017 *Sampling of coal and coke — Part 2:1994 Methods for sampling of coke*. ISO 2309 is being revised in conjunction with ISO 1988 *Hard coal — Sampling*, ISO 9411 *Solid mineral fuels — Mechanical sampling from moving streams — Part 1: Coal* and — Part 2: *Coke*. This revision will be published in eight Parts, and it is intended to implement these Parts as identical British Standards, superseding BS 1017.

A British Standard related to ISO 3310-1 and ISO 3310-2 is BS 410:1986 *Specification for test sieves*.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

**Compliance with a British Standard does not of itself confer immunity from legal obligations.**

## Summary of pages

This document comprises a front cover, an inside front cover, pages i and ii, pages 1 to 4, an inside back cover and a back cover.

This standard has been updated (see copyright date) and may have had amendments incorporated. This will be indicated in the amendment table on the inside front cover.

## 1 Scope and field of application

This International Standard specifies a method of determining the particle size distribution of a sample of coke having a nominal top size of 20 mm or less. Two methods of operation are described:

- a) where a restricted size analysis is required, using two sieves only;
- b) where a complete size analysis is required.

## 2 References

ISO 565, *Test sieves — Woven metal wire cloth, perforated plate and electroformed sheet — Nominal sizes of openings.*

ISO 579, *Coke — Determination of total moisture.*

ISO 1953, *Hard coals — Size analysis.*

ISO 2309, *Coke — Sampling.*

ISO 2591, *Test sieving.*

ISO 3310, *Test sieves — Technical requirements and testing — Part 1: Test sieves of metal wire cloth — Part 2: Test sieves of metal perforated plate.*

## 3 Principle

A sample of coke is subjected to a process of size analysis by a specified procedure, and the results are expressed in terms of the cumulative percentage by mass of the coke remaining on sieves of different sized openings.

## 4 Apparatus

**4.1 Perforated plate sieves**, of round opening size respectively 20 mm and 10 mm.

**4.2 Wire cloth test sieves**, of the following opening sizes:

- 16, 8, 4, 2 and 1 mm;
- 500, 250, 125 and 63  $\mu\text{m}$ .

These sieves are conveniently shaken by means of an appropriate mechanical shaking machine.

The sieves (4.1 and 4.2) shall comply, when selected and during use, with ISO 565, ISO 3310-1 and ISO 3310-2.

**4.3 Lightweight containers**, of metal or plastic material, for the sample and the fractions sieved from it. The largest container shall be capable of holding 20 kg of sample.

**4.4 Weighing machines**, suitable for weighing a mass of up to 30 kg, such that the weighing error does not exceed 0,1 % of the maximum mass of sample or 10 g, whichever is the smaller.

## 5 Sample

The sample shall be representative of the coke and shall be taken as specified in ISO 2309. For coke containing appreciable quantities (over 20 %) above 10 mm, the mass of the sample shall be 20 kg and the whole of this sample shall be used for size analysis. For samples where the nominal top size is 2,8 mm or less, the mass of sample used for size analysis shall be not less than 0,3 kg and preferably not more than 0,5 kg. This quantity shall be taken from the primary sample using one of the following methods of sample division:

- cone divider;
- riffle splitter;
- coning and quartering.

Intermediate masses for the test sample shall be taken according to the nominal top size of the coke.

## 6 Procedure

### 6.1 Restricted size analysis on two sieves

Before commencing the test, dry the coke sample at a temperature of 200 °C (see ISO 579).

Weigh the sample to the nearest 10 g. Place the two sieves (4.1) or two of the sieves (4.2) one above the other in a suitable frame, with the sieve of larger opening size uppermost. Place the receiving tray below the sieve of smaller opening.

Transfer a quantity of the dry coke to the upper sieve, such that it is not choked by the coke. In general, this will mean that not more than 75 % of the sieve is covered by the coke. Shake the sieve by hand (see the note) until no more coke passes through the openings. Remove the top sieve, transfer the oversize to a container of known mass, and carry out the same procedure with the coke remaining on the lower sieve. Replace the empty sieves in the frame. Repeat the process until the whole sample has been treated in this manner, transferring the coke to the appropriate containers after each operation.

Weigh each container with its contents to the nearest 10 g and calculate the total mass of coke which remains on each sieve after the sieving operations.

Transfer the coke which has passed through the lower sieve into the tray to a container of known mass, and weigh.

NOTE Mechanical shaking may be used, provided that its action does not break the coke and that the results are known to be not biased with respect to the results obtained by hand shaking.

### 6.2 Complete size analysis (using a mechanical sieving machine)

NOTE Where a mechanical sieving machine is not available, the procedure specified in ISO 1953 should be adopted.

Before commencing the test, dry the coke sample at a temperature of 200 °C (see ISO 579).

Weigh the sample to an accuracy of 0,1 % It will probably be advisable to carry out the size analysis in two stages if a complete range of openings is to be covered, namely:

- using sieves with 16, 8, 4, 2 and 1 mm openings;
- using sieves with 500, 250, 125 and 63 µm openings.

The diameter of the sieves having openings of 1 mm or more will generally be larger than that of sieves with smaller openings.

When transferring from larger to smaller diameter sieves, it may be necessary to reduce the mass of material to a known proportion and to sieve this known reduced mass on the smaller diameter sieves, repeating the same sieving procedure (see ISO 2591).

Assemble the appropriate sieves in a nest in descending order of size, and fit the receiver. Transfer the sample to the top sieve, fit the lid, and shake the nest of sieves for 5 min.

At the end of this period, clean each sieve in turn, starting with the coarsest mesh sieve, by inverting it over a paper or tray, tapping the side and carefully brushing the uppermost surface of the sieve. Add any loose particles dislodged during brushing to the oversize on the tray or on the paper.

Replace the sieve in the nest, and transfer the material in the tray or on the paper back to the sieve.

Repeat the process of sieving for 5 min, transfer the oversize from each sieve to a container of known mass, adding any material dislodged by brushing, and determine the mass of each fraction.

## 7 Expression of results

### 7.1 Calculation

Record the mass of each size fraction. Calculate the cumulative mass on each sieve, starting with the sieve of largest opening.

The apparent loss, i.e. the difference between the total mass of the sample before and after the size analysis, shall be recorded. Loss in mass means loss of sample, and should not occur. If the loss is not more than 1 % of the original sample mass, it shall be added to the mass of the fraction of smallest size. If the loss is greater than 1 % of the original sample mass, the results of the size analysis shall be rejected.

Convert each cumulative mass to a percentage of the total mass.

If the sample of coke has been sub-divided during the size analysis, the results obtained on the sub-samples shall be multiplied by the ratio of the respective masses in order to relate these results to the original sample of coke. The results shall be reported to the nearest 10 g and 0,1 % (m/m).

For all methods of sieving, the arithmetic mean size may be calculated, using the results of the size analysis of the coke in the following way:

sieve openings:  $a, b, c, d, \dots, h, j, k$   
 cumulative percentages:  $A, B, C, D, \dots, H, J, K$

the symbols being allocated so that  $A = 0\%$  (m/m) and  $K = 100\%$  (m/m) (i.e.  $k = 0$  mm).

Then

$$\text{mean size} = \frac{1}{100} [B(a - c) + C(b - d) + \dots + J(h - k) + 100j]$$

NOTE 1 This formula is greatly simplified when a sieve series of constant interval is used. It is essential that the openings of the sieves in any series be all round or all square. If openings of 1 mm and above are sufficient for the size analysis, a series with either round or square openings may be used. If openings smaller than 1 mm are necessary, only a series of woven wire sieves with square openings shall be used.

NOTE 2 Alternative methods of calculation, or graphical methods, may lead to slightly different results; therefore, when comparing test results from different samples, it is important to adhere to the same method of calculation.

## 7.2 Precision of the method

### 7.2.1 Repeatability

The results of duplicate determinations of size analysis carried out at different times in the same laboratory, by the same operator, with the same apparatus on samples obtained by taking alternate increments from the same consignment of coke,

shall not differ by more than the tolerances given in the table below. The precision is expressed in the table in terms of standard deviation and 95 % confidence limits of a single determination, together with an indication of the tolerance limit of duplicate determinations.

### 7.2.2 Reproducibility

No tolerance is quoted for determinations carried out in different laboratories because the transport of a coke sample involves the risk of breakage and thus alteration of the size distribution.

## 8 Test report

The test report shall include the following particulars:

- the identification of the product tested;
- the reference of the method used;
- the results and the method of expression used;
- the date of test;
- any operation not included in this International Standard or in the International Standards to which reference is made, or regarded as optional.

Cumulative percentage mass retained on sieve	< 5	5-10	10-20	20-40	40-50	50-60	60-70	70-80	80-90	90-95	> 95
Standard deviation	1,75	2,00	2,25	2,50	2,25	2,00	1,75	1,50	1,25	0,75	0,50
95 % limits	3,5	4,0	4,5	5,0	4,5	4,0	3,5	3,0	2,5	1,5	1,0
Tolerance	4,9	5,6	6,3	7,0	6,3	5,6	4,9	4,2	3,5	2,1	1,4





## List of references

See national foreword.

---

---

## **BSI — British Standards Institution**

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

### **Revisions**

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.  
Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

### **Buying standards**

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

### **Information on standards**

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.  
Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.  
Tel: 020 8996 7002. Fax: 020 8996 7001.

### **Copyright**

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager.  
Tel: 020 8996 7070.