



Standard Specification for Steel Forgings, Alloy, for Carburizing Applications¹

This standard is issued under the fixed designation A 837/A 837M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers alloy steel forgings for carburizing applications.

1.2 Forgings are considered weldable under proper conditions. Welding technique is of fundamental importance and it is presupposed that welding procedure and inspection shall be in accordance with approved methods for the class of material used.

1.3 This specification is expressed in both inch-pound units and in SI units. However, unless the order specifies the applicable *M* specification designation (SI units), the material shall be furnished to inch-pound units.

1.4 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

2. Referenced Documents

2.1 ASTM Standards:

A 275/A 275M Test Method for Magnetic Particle Examination of Steel Forgings²

A 388/A 388M Practice for Ultrasonic Examination of Heavy Steel Forgings²

A 788 Specification for Steel Forgings, General Requirements²

E 527 Practice for Numbering Metals and Alloys (UNS)³

3. Ordering Information

3.1 Instructions for purchasing forgings to this specification are to be in accordance with Specification A 788.

3.2 In addition to the basic requirements of this specification, certain supplementary requirements are listed at the end of this specification. These supplementary requirements may

be applicable when additional control, testing, or examination is required to meet end use requirements.

4. Heat Treatment

4.1 The forgings shall be given a normalize or normalize and temper heat treatment.

5. Machining

5.1 Rough machining before heat treatment may be performed at the option of the manufacturer.

6. Chemical Composition

6.1 The steel shall conform to the requirements for chemical composition prescribed in Table 1 unless otherwise modified in accordance with Supplementary Requirement S4.

7. Mechanical Properties

7.1 Hardness:

7.1.1 Maximum hardness of the forgings shall be 229 BHN.

7.1.2 Hardness tests shall be taken on prepared surfaces of the forging after machining to the purchaser's ordering requirements.

7.1.3 Number and Location of Tests:

7.1.3.1 For forgings not intended for gear applications, the number and location of hardness tests shall be by agreement between the purchaser and forger.

7.1.3.2 For gear applications on each forging 8 in. [200 mm] and over in diameter, four Brinell hardness tests shall be made on the outside surface of that portion of the forging on which teeth will be cut two tests being made on each helix 180° apart, and the tests on the two helices shall be 90° apart. On each forging under 8 in. [200 mm] in diameter two Brinell hardness tests shall be made, one on each helix 180° apart. On hollow, cylindrical forgings, one hardness test on each end shall be taken 180° apart. Hardness tests shall be performed at the quarter-face width of the tooth-portion diameter.

8. Other Requirements

8.1 Forgings supplied to this material specification shall conform to the latest issue of Specification A 788.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.06 on Steel Forgings and Billets.

Current edition approved June 10, 2003. Published July 2003. Originally approved in 1985. Last previous edition approved in 2001 as A 837 – 91 (2001).

² Annual Book of ASTM Standards, Vol 01.05.

³ Annual Book of ASTM Standards, Vol 01.01.

*A Summary of Changes section appears at the end of this standard.

TABLE 1 Grade Designations and Chemical Compositions

		Chemical Composition, Ranges and Limits, %								
UNS Designation ^A	Grade Designation ^B	Carbon	Man-ganese	Phos-phorus, max	Sulfur, max	Silicon ^C	Nickel	Chro-mium	Molyb-denum	Copper, max
G33106	E3310	0.08–0.13	0.45–0.60	0.025	0.025	0.15–0.35	3.25–3.75	1.40–1.75	0.10 max	0.35
G43200	4320	0.17–0.22	0.45–0.65	0.035	0.040	0.15–0.35	1.65–2.00	0.40–0.60	0.20–0.30	0.35
G46200	4620	0.17–0.22	0.45–0.65	0.035	0.040	0.15–0.35	1.65–2.00	0.25 max	0.20–0.30	0.35
G48150	4815	0.13–0.18	0.40–0.60	0.035	0.040	0.15–0.35	3.25–3.75	0.25 max	0.20–0.30	0.35
G86200	8620	0.18–0.23	0.70–0.90	0.035	0.040	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25	0.35
G93100	9310	0.07–0.13	0.40–0.70	0.035	0.040	0.15–0.35	2.95–3.55	1.00–1.45	0.08–0.15	0.35
S41000	410	0.15 max	1.00 max	0.040	0.030	1.00 max	0.50 max	11.50–13.50	0.10 max	0.35

^A New designation established in accordance with Practice E 527.

^B Grade designations correspond to the respective Practice E 527.

^C When vacuum carbon deoxidation is used, silicon maximum shall be 0.10 %.

8.2 Specification A 788 covers forging terminology, melting processes, chemical analysis test methods, product analysis tolerances, mechanical testing methods, repair welding restrictions, marking, and certification requirements.

9. Keywords

9.1 alloy steel forgings; carburizing

SUPPLEMENTARY REQUIREMENTS

The following supplementary requirements shall apply only when specified by the purchaser on the order and agreed to by the manufacturer.

S1. Rough Turning and Boring

S1.1 The position of rough turning and boring in the sequence of manufacturing operations is specified.

S2. Magnetic Particle Examination

S2.1 Magnetic particle examination shall be specified in accordance with Test Method A 275/A 275M. Reporting and acceptance standards shall be a matter of agreement.

S3. Ultrasonic Examination

S3.1 Ultrasonic examination shall be specified in accordance with Practice A 388. Reporting and acceptance standards shall be a matter of agreement.

S4. Phosphorous and Sulfur Restriction

S4.1 Phosphorus shall not exceed 0.015 %, and the sulfur shall not exceed 0.018 % for all classes when determined in accordance with the heat analysis requirements of Specification A 788.

S5. Vacuum Degassing

S5.1 Vacuum treatment of the molten steel prior to or during the pouring of the ingot is required.

SUMMARY OF CHANGES

Committee A01 has identified the location of the following changes since A 837/A 837M – 91 (2001) that may impact the use of this standard.

(1) Added metric units in section 7.1.3.2.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).